

What is claimed is:

1. A soldering method comprising the steps of:

bonding a first electronic component having electrodes
5 plated with a material containing lead to one surface of an
interconnect substrate through solder containing no lead;

flow-soldering to bond a second electronic component to
the other surface of the interconnect substrate; and

heating a joint section between the first electronic
10 component and the interconnect substrate at the same time as
or after the step of flow-soldering to melt the joint section.

2. The soldering method as defined in claim 1,

wherein the step of heating the joint section is performed
15 at the same time as the step of flow soldering.

3. The soldering method as defined in claim 1,

wherein the step of heating the joint section is performed
after the step of flow soldering.

20 4. The soldering method as defined in claim 1,

wherein the step of heating the joint section is performed
both at the same time as and after the step of flow soldering.

25 5. The soldering method as defined in claim 1,

wherein the step of heating the joint section is performed
by at least one of radiant heat and a hot blast.

6. The soldering method as defined in claim 1,
wherein the first electronic component is bonded to one
surface of the interconnect substrate by reflow soldering.

5

7. The soldering method as defined in claim 1,
wherein the first electronic component is bonded to one
surface of the interconnect substrate by hand soldering.

10
15
20
25
30
35
40
45
50
55
60
65
70
75
80
85
90
95
100
105
110
115
120
125
130
135
140
145
150
155
160
165
170
175
180
185
190
195
200
205
210
215
220
225
230
235
240
245
250
255
260
265
270
275
280
285
290
295
300
305
310
315
320
325
330
335
340
345
350
355
360
365
370
375
380
385
390
395
400
405
410
415
420
425
430
435
440
445
450
455
460
465
470
475
480
485
490
495
500
505
510
515
520
525
530
535
540
545
550
555
560
565
570
575
580
585
590
595
600
605
610
615
620
625
630
635
640
645
650
655
660
665
670
675
680
685
690
695
700
705
710
715
720
725
730
735
740
745
750
755
760
765
770
775
780
785
790
795
800
805
810
815
820
825
830
835
840
845
850
855
860
865
870
875
880
885
890
895
900
905
910
915
920
925
930
935
940
945
950
955
960
965
970
975
980
985
990
995

8. The soldering method as defined in claim 1, further
comprising:

a step of preheating the joint section before the step
of flow soldering.

9. The soldering method as defined in claim 1,
wherein the solder containing no lead is formed of at
least one material selected from a group consisting of tin,
silver, copper, zinc, and bismuth.

10. The soldering method as defined in claim 1,
wherein at least the step of heating the joint section
is performed in a chamber.

11. A method of fabricating an electronic circuit module,
wherein the first and second electronic components are
mounted on the interconnect substrate by the soldering method
as defined in claim 1.

12. A soldering device comprising:

a flow soldering section, when a first electronic component having electrodes plated with a material containing lead is bonded to one surface of an interconnect substrate through solder containing no lead, bonds a second electronic component to the other surface of the interconnect substrate,

wherein the flow soldering section includes a heater disposed on the side of a surface of the interconnect substrate to which the first electronic component is bonded, to melt a joint section between the first electronic component and the interconnect substrate.

13. The soldering device as defined in claim 12,

wherein the flow soldering section has a solder supplying section disposed on the side of the other surface of the interconnect substrate; and

wherein the heater is disposed above the solder supplying section.

14. The soldering device as defined in claim 12,

wherein the flow soldering section has a solder supplying section disposed on the side of the other surface of the interconnect substrate; and

wherein the heater is disposed downstream from the solder supplying section in a direction in which the interconnect substrate is transferred.

15. The soldering device as defined in claim 12,

wherein the flow soldering section has a solder supplying section disposed on the side of the other surface of the interconnect substrate; and

wherein the heater is disposed above the solder supplying section or downstream from the solder supplying section in a direction in which the interconnect substrate is transferred.

16. The soldering device as defined in claim 12, comprising a plurality of the heaters,

wherein the flow soldering section has a solder supplying section disposed on the side of the other surface of the interconnect substrate;

wherein part of the heaters is disposed above the solder supplying section; and

wherein another part of the heaters is disposed downstream from the solder supplying section in a direction in which the interconnect substrate is transferred.

17. The soldering device as defined in claim 12, comprising: a plurality of the heaters, wherein at least one of the heaters is a far infrared heater.

18. The soldering device as defined in claim 12, further comprising a fan.

19. The soldering device as defined in claim 12, further comprising:

a reflow soldering section for bonding the first electronic component to one surface of the interconnect substrate.

20. The soldering device as defined in claim 12, further comprising:

a second heater for preheating the joint section before flow soldering.

21. The soldering device as defined in claim 12, further comprising:

a chamber in which at least the flow soldering section is disposed.

22. A device of fabricating an electronic circuit module comprising the soldering device as defined in claim 12,

wherein the first and second electronic components are mounted on the interconnect substrate.